



## Material - ASTM B124 C62300

## Standard Specification for Copper and Copper Alloy Forging Rod, Bar and Shapes

**Group - Non-Ferrous Copper Alloy** 

Sub Group - ASTM B124 Copper and Copper Alloy Forging Rod, Bar and Shape Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Rod, Bar and Shape

Chemical Composition			Heat Treatment	
Aluminium	Al %	8.500 - 10.000		
Iron	Fe %	2.000 - 4.000		
Manganese	Mn %	0.500 max.		
Ni + Co	Ni% + Co%	1.000 max.	As Drawn or Stress Relieving or Hot Rolled	
Silicon	Si %	0.250 max.		
Tin	Sn %	0.600 max.		
Cu + Ag	Cu% + Ag%	Balance		
-	-	-		
-	-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	515 min.
-	-	-	Yield Strength in Mpa	205 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
C62300	UNS	USA	Rod, Bar, Tube and Shapes	
B150 C62300	ASTM	USA	Rod, Bar and Shapes	
SB-150 C62300	ASME	USA	Rod, Bar and Shapes	
SB-283 C62300	ASME	USA	Forging	
4635	SAE	USA	Bars, Rods and Forgings	
CA623	SAE	USA	Casting	
87Cu-9Al-3Fe	SAE	USA	Bars, Rods and Forgings	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.