

## Material - ASTM B124 C63200

Standard Specification for Copper and Copper Alloy Forging Rod, Bar and Shapes Group - Non-Ferrous Copper Alloy

Sub Group - Standard Specification for Copper and Copper Alloy Forging Rod, Bar and Shapes Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Rod, Bar and Shape

| Chemical Composition |           |               | Heat Treatment                      |               |
|----------------------|-----------|---------------|-------------------------------------|---------------|
| Aluminium            | Al %      | 8.700 - 9.500 |                                     |               |
| Iron                 | Fe %      | 3.500 - 4.300 |                                     |               |
| Manganese            | Mn %      | 1.200 - 2.000 | As Drawn or Hardening and Tempering |               |
| Ni + Co              | Ni% + Co% | 4.000 - 4.800 |                                     | and Tempering |
| Lead                 | Pb %      | 0.020 max.    |                                     |               |
| Silicon              | Si %      | 0.100 max.    |                                     |               |
| Copper               | Cu %      | Balance       |                                     |               |
| -                    | -         | -             |                                     |               |
| -                    | -         | -             | Mechanical Properties               |               |
| -                    | -         |               | Tensile Strength in Mpa             | 620 min.      |
| -                    | -         | -             | Yield Strength in Mpa               | 275 min.      |
| -                    | -         | -             | Elongation in %                     | 15 min.       |
| -                    | -         | -             | Reduction of Area in %              | -             |
| -                    | -         | -             | Hardn <mark>ess in BH</mark> N      | -             |
| -                    | -         | -             | Impac <mark>t in Joule</mark>       | -             |

| Cross Reference Table |          |         |                              |  |
|-----------------------|----------|---------|------------------------------|--|
| Material              | Standard | Country | Grade Belong to the Industry |  |
| C63200                | UNS      | USA     | Rod, Bar, Tube and Shapes    |  |
| B150 C63200           | ASTM     | USA     | Rod, Bar and Shape           |  |
| B283 C63200           | ASTM     | USA     | Forging                      |  |
| SB-150 C63200         | ASME     | USA     | Rod, Bar and Shape           |  |
| SB-171 C63200         | ASME     | USA     | Plate and Sheet              |  |
| SB-283 C63200         | ASME     | USA     | Forging                      |  |
| -                     | -        | -       | -                            |  |

## Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

## ONE STOP SOLUTION FOR METAL PARTS