

Material - ASTM B124 UNS C36500

Standard Specification for Copper and Copper Alloy Forging Rod, Bar and Shapes

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B124 Copper and Copper Alloy Forging Rod, Bar and Shapes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Rod, Bar and Shape

| Chemical Composition | | Heat Treatment | |
|----------------------|---|--|---|
| Pb % | 0.250 - 0.700 | | |
| Sn % | 0.250 max. | | |
| Fe % | 0.150 max. | | |
| Zn % | Balance | Normalizing or Annealing or Tempering | g or Tempering |
| Cu % | 58.000 - 61.000 | | |
| - | - | | |
| - | - | | |
| - | - | | |
| - | - | Mechanical Properties | |
| - | - | Tensile Strength in Mpa | 344 min. |
| - | - | Yield Strength in Mpa | - |
| - | - | Elongation in % | - |
| - | - | Reduction of Area in % | - |
| - | - | Hardness in BHN | - |
| - | - | Impac <mark>t in Joule</mark> | - |
| | Sn % Fe % Zn % Cu % - - - - - - - - - - - - - - - - - - - | Sn % 0.250 max. Fe % 0.150 max. Zn % Balance Cu % 58.000 - 61.000 - - - <td>Sn % 0.250 max. Fe % 0.150 max. Zn % Balance Cu % 58.000 - 61.000 - -</td> | Sn % 0.250 max. Fe % 0.150 max. Zn % Balance Cu % 58.000 - 61.000 - - |

| Cross Reference Table | | | | |
|-----------------------|----------|-----------|------------------------------|--|
| Material | Standard | Country | Grade Belong to the Industry | |
| B171 C36500 | ASTM | USA | Plate and Sheet | |
| B283 C36500 | ASTM | USA | Forging | |
| SB-171 C36500 | ASME | USA | Plate and Sheet | |
| SB-283 C36500 | ASME | USA | Forging | |
| 365 | AS | Australia | Forging | |
| C36500 | AS | Australia | Forging | |
| C36500 | UNS | USA | Rod, Bar and Shapes | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS