



## Material - ASTM B124 UNS C48200

Standard Specification for Copper and Copper Alloy Forging Rod, Bar, and Shapes

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B 124/B 124M Copper and Copper Alloy Forging Rod, Bar, and Shapes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Forging Rod, Bar and Shape

Chemical Composition			Heat Treatment	
Lead	Pb %	0.400 - 1.000	Normalizing or Annealing or Tempering	
Tin	Sn %	0.500 - 1.000		
Iron	Fe %	0.100 max.		
Copper	Cu %	59.000 - 62.000		
Zinc	Zn %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	-
			Yield Strength in Mpa	-
			Elongation in %	-
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C48200	UNS	USA	Forging Rod, Bar and Shape
B21 C48200	ASTM	USA	Rod, Bar and Shape
B283 C48200	ASTM	USA	Forging
SB-283 C48200	ASME	USA	Forging
CW714R	ONORM	Australia	Forging
CW714R	BDS	Bulgaria	Forging
CW714R	CSN	Czech Republic	Forging

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.