



## Material - ASTM B145-4B

## **Standard Specification for Copper Alloy Sand Casting for General Applications**

**Group - Non-Ferrous Copper Alloy** 

Sub Group - ASTM B145 Copper Alloy Sand Casting for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.005 max.		
Iron	Fe %	0.300 max.		
Ni + Co	Ni% + Co%	1.000 max.	As-Cast	
Phosphorus	P %	0.030 max.		
Lead	Pb %	5.000 - 7.000		
Sulphur	S %	0.080 max.		
Antimony	Sb %	0.250 max.		
Silicon	Si %	0.005 max.		
Tin	Sn %	3.300 - 4.200	Mechanical Properties	
Zinc	Zn %	5.000 - 8.000	Tensile Strength in Mpa	207 min.
Copper	Cu %	82.000 - 83.800	Yield Strength in Mpa	90 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
C83800	UNS	USA	Rod, Bar, Tube and Shapes	
C83800	SAE	USA	Casting	
B30 C83800	ASTM	USA	Casting	
B505 C83800	ASTM	USA	Casting	
CA838	SAE	USA	Casting	
B584 C83800	ASTM	USA	Casting	
SB-505 C83800	ASME	USA	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.