



Material - ASTM B148 Aluminum Bronze UNS C95410

Standard Specification for Alumium - Bronze Sand Castings

Group - Non-Ferrous Alumium Alloy

Sub Group - ASTM B148 Alumium - Bronze Sand Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Ni + Cu	Ni% + Cu%	1.500 - 2.500	As-Cast or Solution Annealing or Normalizing	
Manganese	Mn %	0.500 max.		
Iron	Fe %	3.000 - 5.000		
Aluminium	Al %	10.000 - 11.500		
Copper	Cu %	83.000 min.		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	515 min.
			Yield Strength in Mpa	205 min.
			Elongation in %	12 min.
			Reduction of Area in %	-
			Hardness in BHN	150 min.
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B176 C95410	ASTM	USA	Casting
B271 C95410	ASTM	USA	Casting
B30 C95410	ASTM	USA	Ingot and Casting
B505 C95410	ASTM	USA	Casting
SB-148 C95410	ASME	USA	Casting
SB-505 C95410	ASME	USA	Casting
CACIn702	KS	Korea	Ingot and Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.