



Material - ASTM B148 Grade A

Standard Specification for Aluminum-Bronze Sand Casting

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B148 Aluminum-Bronze Sand Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|---------------|-------------------------|----------|
| Aluminium | Al % | 8.500 - 9.500 | As-Cast | |
| Iron | Fe % | 2.500 - 4.000 | | |
| Copper | Cu % | 86.000 min. | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| | | | Mechanical Properties | |
| - | - | - | Tensile Strength in Mpa | 450 min. |
| - | - | - | Yield Strength in Mpa | 170 min. |
| - | - | - | Elongation in % | 20 min. |
| - | - | - | Reduction of Area in % | - |
| - | - | - | Hardness in HB | 110 min. |
| - | - | - | Impact in Joule | - |

| Cross Reference Table | | | |
|-----------------------|----------|---------|------------------------------|
| Material | Standard | Country | Grade Belong to the Industry |
| C95200 | UNS | USA | Rod, Bar, Tube and Shapes |
| B148 C95200 | ASTM | USA | Casting |
| SB-148 C95200 | ASME | USA | Casting |
| SB-148 Grade A | ASME | USA | Casting |
| C95200 | SAE | USA | Casting |
| CA952 | SAE | USA | Casting |
| CACIn701 | KS | Korea | Ingot and Casting |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.