

Material - ASTM B150 UNS C61300

Standard Specification for Alumium Bronze Road, Bar and Shapes

Group - Non-Ferrous Alumium Alloy

Sub Group - ASTM B150 Alumium Bronze Road, Bar and Shapes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Rod, Bar and Shape

Chemical Composition		Heat Treatment	
Р%	0.015 max.		
Pb %	0.010 max.		
Zn %	0.100 max.	As Drawn or Stress Relieving	
Sn %	0.200 - 0.500		Relieving
Si %	0.100 max.		
Mn %	0.200 max.		
Ni% + Cu%	0.150 max.		
Fe %	2.000 - 3.000		
Al %	6.000 - 7.500	Mechanical Properties	
Cu %	Balance	Tensile Strength in Mpa	485 min.
-	-	Yield Strength in Mpa	220 min.
-	-	Elongation in %	30 min.
-	-	Reduction of Area in %	-
-	-	Hardness in BHN	-
-	-	Impac <mark>t in Joule</mark>	-
	P % Pb % Zn % Sn % Si % Mn % Ni% + Cu% Fe % Al % Cu % - - - -	P % 0.015 max. Pb % 0.010 max. Zn % 0.100 max. Sn % 0.200 - 0.500 Si % 0.100 max. Mn % 0.200 max. Ni% + Cu% 0.150 max. Fe % 2.000 - 3.000 Al % 6.000 - 7.500 Cu % Balance - - - - - -	P % 0.015 max. Pb % 0.010 max. Zn % 0.100 max. Sn % 0.200 - 0.500 Si % 0.100 max. Mn % 0.200 max. Ni% + Cu% 0.150 max. Fe % 2.000 - 3.000 Al % 6.000 - 7.500 Mechanical Pro Cu % Balance Tensile Strength in Mpa - - - Elongation in % - - - - - - - - - -

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
B100 C61300	ASTM	USA	Plate and Sheet	
B111 C61300	ASTM	USA	Tubes	
B169 C61300	ASTM	USA	Sheet, Strip and Bar	
B171 C61300	ASTM	USA	Plate and Sheet	
F467 C61300	ASTM	USA	Bolts, Screws and Studs	
SB-111 C61300	ASME	USA	Tubes	
SB-150 C61300	ASME	USA	Rod, Bar and Shapes	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS