



Material - ASTM B171 C46400

Standard Specification for Copper-Alloy Plate and Sheet for Pressure Vessels, Condensers and Heat Exchangers

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B171 Copper-Alloy Plate and Sheet for Pressure Vessels, Condensers and Heat Exchangers

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Plate and Sheet

Chemical Composition			Heat Treatment	
Iron	Fe %	0.100 max.	Normalizing or Annealing or Tempering	
Lead	Pb %	0.200 max.		
Tin	Sn %	0.500 - 1.000		
Copper	Cu %	59.000 - 62.000		
Zinc	Zn %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	345 min.
			Yield Strength in Mpa	125 - 140
			Elongation in %	35 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuZn39Sn	IS	India	Plate
B283 C46400	ASTM	USA	Forging
CZ 133	BS	British	Rod and Section
SB-171 C46400	ASME	USA	Plate and Sheet
SB-283 C46400	ASME	USA	Forging
F467 C46400	ASTM	USA	Nut
CuZn38Sn1	ISO	International	Rod and Bar

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.