

Material - ASTM B171 C61300

Standard Specification for Copper-Alloy Plate and Sheet for Pressure Vessels, Condensers and Heat Exchangers

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B171 Copper-Alloy Plate and Sheet for Pressure Vessels, Condensers and Heat Exchangers Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Plate and Sheet

Chemical Composition			Heat Treatment	
Aluminium	Al %	6.000 - 7.500		
Iron	Fe %	2.000 - 3.000		
Manganese	Mn %	0.200 max.	As Drawn or Stress Relieving	
Ni + Co	Ni% + Co%	0.150 max.		
Phosphorus	P %	0.015 max.		
Lead	Pb %	0.010 max.		
Silicon	Si %	0.100 max.		
Tin	Sn %	0.200 - 0.500		_
Zinc	Zn %	0.100 max.	Mechanical Properties	
Copper	Cu %	Balance	Tensile Strength in Mpa	450 - 515
-	-	-	Yield Strength in Mpa	180 - 250
-	-	-	Elongation in %	30 - 35
-	-	_	Reduction of Area in %	-
-	-	-	Hardness in BHN	
-	-		Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
C61300	UNS	USA	Rod, Bar, Tube and Shapes	
B100 C61300	ASTM	USA	Plate and Sheet	
B111 C61300	ASTM	USA	Tubes	
B169 C61300	ASTM	USA	Sheet, Strip and Bar	
F467 C61300	ASTM	USA	Bolts, Screws and Studs	
SB-111 C61300	ASME	USA	Tubes	
SB-150 C61300	ASME	USA	Rod, Bar and Shapes	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.