



Material - ASTM B187 C11000

Standard Specification for Copper, Bus Bar, Rod and Shapes for General Purpose

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B187 Copper, Bus Bar, Rod and Shapes for General Purpose Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Rod, Bar and Shapes

Chemical Composition			Heat Treatment	
Cu + Ag	Cu% + Ag%	99.900 min.		
-	-	-		
-	-	-	Normalizing or Annealing or Tempering	
-	-			
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	154.500 - 698.200
-	-		Yield Strength in Mpa	55 - 367
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRB	30 - 97
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
C11000	UNS	USA	Rod, Bar, Tube and Shapes	
B133 C11000	ASTM	USA	Rod, Bar and Shape	
B152 C11000	ASTM	USA	Sheet, Strip, Plate and Rolled Bar	
B188 C11000	ASTM	USA	Pipe and Tube	
SB-152 C11000	ASME	USA	Sheet, Strip, Plate and Rolled Bar	
SB-187 C11000	ASME	USA	Rod, Bar and Shapes	
SB-283 C11000	ASME	USA	Forging	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.