

## Material - ASTM B224 C14700

## Standard Specification for Copper and Copper-Alloy

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B224 Copper and Copper-Alloy

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Phosphorus	Р%	0.002 - 0.005		
Sulphur	S %	0.200 - 0.500		
Copper	Cu %	99.90 min.	Normalizing or Annealing or Tempering	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	154.500 - 698.200
-	-	-	Yield Strength in Mpa	55 - 367
	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
C14700	UNS	USA	Rod, Bar, Tube and Shapes	
B283 C14700	ASTM	USA	Forging	
B301 C14700	ASTM	USA	Rod, Bar, Wire and Shapes	
SB-283 C14700	ASME	USA	Forging	
-	-	-	-	
-	-	-	-	
-	-	-	-	

## Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

## ONE STOP SOLUTION FOR METAL PARTS