

Material - ASTM B240 AC41A

Standard Specification for Zinc and Zinc-Aluminum (ZA) Alloys in Ingot Form for Foundry Group - Non-Ferrous Zinc Alloy

Sub Group - ASTM B240 Zinc and Zinc-Aluminum (ZA) Alloys in Ingot Form for Foundry and Die Castings Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	3.900 - 4.300		
Cadmium	Cd %	0.003 max.	As-Cast or Aging	
Copper	Cu %	0.700 - 1.100		
Iron	Fe %	0.035 max.		
Magnesium	Mg %	0.030 - 0.060		
Lead	Pb %	0.004 max.		
Tin	Sn %	0.0015 max.		
Zinc	Zn %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	328 min.
-	-	-	Yield Strength in Mpa	228 min.
-	-	-	Elongation in %	7 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	91 min.
-	-	-	Impac <mark>t in Joule</mark>	65 min. @RT

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
Zamak 5	ANSI/AA	USA	Casting	
ZP5	ISO	International	Casting	
Z33531	UNS	USA	Ingot and Casting	
B86 Alloy 5	ASTM	USA	Casting	
B86 Zamak 5	ASTM	USA	Casting	
B86 AC41A	ASTM	USA	Casting	
B240 Zamak 5	ASTM	USA	Ingot and Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS