



Material - ASTM B240 ZA12

Standard Specification for Zinc and Zinc-Aluminum (ZA) Alloys in Ingot Form for Foundry and Die Castings

Group - Non-Ferrous Zinc Alloy

Sub Group - ASTM B240 Zinc and Zinc-Aluminum (ZA) Alloys in Ingot Form for Foundry and Die Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	10.800 - 11.500	As-Cast or Aging	
Cadmium	Cd %	0.005 max.		
Copper	Cu %	0.500 - 1.200		
Iron	Fe %	0.050 max.		
Magnesium	Mg %	0.020 - 0.030		
Lead	Pb %	0.005 max.		
Tin	Sn %	0.002 max.		
Zinc	Zn %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	276 - 404
-	-	-	Yield Strength in Mpa	211 - 320
-	-	-	Elongation in %	1 - 7
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	89 - 100
-	-	-	Impact in Joule	25 - 29 @RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
ZA-12	ANSI/AA	USA	Casting
B86 ZA12	ASTM	USA	Casting
ZP1110	ISO	International	Casting
ZP12	ISO	International	Casting
Z35631	UNS	USA	Casting
Z35633	UNS	USA	Casting
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.