



## Material - ASTM B271 C87500

## Standard Specification for Copper-Base Alloy Centrifugal Casting

**Group - Non-Ferrous Copper Alloy** 

Sub Group - ASTM B271 Copper-Base Alloy Centrifugal Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry - Casting** 

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.500 max.		
Lead	Pb %	0.090 max.		
Silicon	Si %	3.000 - 5.000		
Zinc	Zn %	12.000 - 16.000	As-Cast	
Copper	Cu %	79.000 min.		
-	-			
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	414 min.
-	-		Yield Strength in Mpa	165 min.
-	-		Elongation in %	16 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-		Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
C87500	UNS	USA	Rod, Bar, Tube and Shapes	
B30 C87500	ASTM	USA	Ingot and Casting	
C87500	SAE	USA	Casting	
CA875	SAE	USA	Casting	
B584 C87500	ASTM	USA	Casting	
SB-584 C87500	ASME	USA	Casting	
CACIn802	KS	Korea	Ingot and Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.