

## **ASTM B271 Tin Bronze and Leaded Tin Bronze UNS C92300**

Standard Specification for Copper-Base Alloy Centrifugal Castings

**Group - Non-Ferrous Copper Alloy** 

Sub Group - ASTM B271 Copper-Base Alloy Centrifugal Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod, Bar, Tube and Shapes

Chemical Composition			Heat Treatment	
Tin	Sn %	7.500 - 9.000	As-Cast	
Lead	Pb %	0.300 - 1.000		
Zinc	Zn %	2.500 - 5.000		
Iron	Fe %	0.250 max.		
Ni + Co	Ni% + Co%	1.000 max.		
Aluminium	Al %	0.005 max.		
Silicon	Si %	0.005 max.		
Antimony	Sb %	0.250 max.		
Sulphur	S %	0.050 max.	Mechanical Properties	
Phosphorus	P %	0.050 max.	Tensile Strength in Mpa	234 min.
Copper	Cu %	85.000 - 89.000	Yield Strength in Mpa	110 min.
-	-	-	Elongation in %	22 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
B30 2B	ASTM	USA	Ingot and Casting		
B30 C92300	ASTM	USA	Ingot and Casting		
B271 C92300	ASTM	USA	Casting		
B505 C92300	ASTM	USA	Casting		
B584 C92300	ASTM	USA	Casting		
SB-505 C92300	ASME	USA	Casting		
CA923	SAE	USA	Ingot and Casting		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.