

Material - ASTM B275 380.0

Standard Practice for Codification of Certain Nonferrous Metals and Alloys, Cast and Wrought

Group - Non-Ferrous Alumium Alloy

Sub Group - ASTM B275 Codification of Certain Nonferrous Metals and Alloys, Cast and Wrought Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	3.000 - 4.000	As-Cast	
Iron	Fe %	2.000 max.		
Magnesium	Mg %	0.100 max.		
Manganese	Mn %	0.500 max.		
Nickel	Ni %	0.500 max.		
Silicon	Si %	7.500 - 9.500		
Tin	Sn %	0.350 max.		
Zinc	Zn %	3.000 max.		•
Other	Ot%	0.500 max.	Mechanical Properties	
Aluminium	Al %	Balance	Tensile Strength in Mpa	315 min.
-	-	-	Yield Strength in Mpa	160 min.
-	-	-	Elongation in %	2.5 min.
-	-		Reduction of Area in %	-
-	-	-	Hardn <mark>ess in HB</mark>	-
-	-		Impact in Joule	-

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
A03800	UNS	USA	Casting	
380	AA	USA	Casting	
A 275 SC84B	ASTM	USA	Casting	
B 85 380.0	ASTM	USA	Casting	
B 85 SC84B	ASTM	USA	Casting	
A03800	SAE	USA	Casting	
380.0	NBR	Brazil	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.