



Material - ASTM B283 C63000

Standard Specification for Copper and Copper-Alloy Die Forgings

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B283 Copper and Copper-Alloy Die Forgings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Forging

Chemical Composition			Heat Treatment	
Aluminium	Al %	9.000 - 11.000	As Drawn or Stress Relieving or Hot Rolled	
Iron	Fe %	2.000 - 4.000		
Manganese	Mn %	1.500 max.		
Ni + Co	Ni% + Co%	4.000 - 5.500		
Silicon	Si %	0.250 max.		
Tin	Sn %	0.200 max.		
Zinc	Zn %	0.300 max.		
Copper	Cu %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	655 min.
-	-	-	Yield Strength in Mpa	330 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRB	90 min.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C63000	UNS	USA	Rod, Bar, Tube and Shapes
B124 C63000	ASTM	USA	Rod, Bar and Shape
B171 C63000	ASTM	USA	Plate and Sheet
SB-150 C63000	ASME	USA	Rod, Bar and Shape
SB-171 C63000	ASME	USA	Plate and Sheet
CA630	SAE	USA	Casting
CuAl10Ni5Fe4	ISO	International	Rod and Bar

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.