



Material - ASTM B30 C93600

Standard Specification for Copper Alloys Ingot and Casting

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B30 Copper Alloys Ingot and Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.005 max.	As-Cast	
Iron	Fe %	0.150 max.		
Ni + Co	Ni% + Co%	0.800 max.		
Phosphorus	P %	0.050 max.		
Lead	Pb %	11.300 - 13.000		
Sulphur	S %	0.080 max.		
Antimony	Sb %	0.500 max.		
Silicon	Si %	0.005 max.		
Zinc	Zn %	1.000 max.	Mechanical Properties	
Copper	Cu %	79.000 - 82.000	Tensile Strength in Mpa	221 min.
-	-	0	Yield Strength in Mpa	110 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
C93600	UNS	USA	Rod, Bar, Tube and Shapes	
B66 C93600	ASTM	USA	Casting	
B271 C93600	ASTM	USA	Casting	
B505 C93600	ASTM	USA	Casting	
CACIn406	KS	Korea	Ingot and Casting	
SB-271 C93600	ASME	USA	Casting	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.