



Material - ASTM B472 N06230

Standard Specification for Nickel and Nickel-Related Alloys Billets and Bars for Reforging Group - Non-Ferrous Nickel Alloys

Sub Group - ASTM B472 N06230 Nickel and Nickel-Related Alloys Billets and Bars for Reforging

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Billets and Bars for Reforging

Chemical Composition			Heat Treatment	
Carbon	C %	0.005 - 0.150	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.250 - 0.750		
Manganese	Mn %	0.300 - 1.000		
Chromium	Cr %	20.000 - 24.000		
Cobalt	Co %	5.000 max.		
Molybdenum	Mo %	1.000 - 3.000		
Sulphur	S %	0.015 max.		
Phosphorus	P %	0.030 max.		
Aluminium	Al %	0.500 max.		
Iron	Fe %	3.000 max.		
Boron	B %	0.015 max.	Mechanical Properties Tensile Strength in Mpa 760 min. Yield Strength in Mpa 310 min. Elongation in % 40 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
Lanthanum	La %	0.005 - 0.050		
Tungsten	W %	13.000 - 15.000		
Nickel	Ni %	Balance		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
UNS N06230	UNS	USA	Sheet, Strip and Plate
INCONEL alloy N06230	Gravity	India	Sheet, Strip and Plate
B435 N06230	ASTM	USA	Plate, Sheet and Strip
B564 N06230	ASTM	USA	Forging
SB-435 N06230	ASME	USA	Plate, Sheet and Strip
SB-564 N06230	ASME	USA	Forging
SB-572 N06230	ASME	USA	Sheet, Strip and Plate

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.