



Material - ASTM B505 Nickel-Tin Bronze UNS C94700

Standard Specification for Copper Alloy Continuous Casting

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B505 / 505M Copper Alloys for Continuous Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod, Bar, Tube and Shapes

Chemical Composition			Heat Treatment	
Tin	Sn %	4.500 - 6.000	As-Cast or Solution Annealing	
Lead	Pb %	0.100 max.		
Zinc	Zn %	1.000 - 2.500		
Ni + Cu	Ni% + Cu%	4.500 - 6.000		
Iron	Fe %	0.250 max.		
Antimony	Sb %	0.150 max.		
Sulphur	S %	0.050 max.		
Phosphorus	P %	0.050 max.		
Aluminium	Al %	0.005 max.		
Manganese	Mn %	0.200 max.		
Silicon	Si %	0.005 max.	Mechanical Properties	
Copper	Cu %	85.000 - 90.000	Tensile Strength in Mpa	310 min.
-	-	-	Yield Strength in Mpa	138 min.
-	-	-	Elongation in %	25 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B292-A	ASTM	USA	Casting
B30 C94700	ASTM	USA	Ingot and Casting
B505 C94700	ASTM	USA	Casting
B584 C94700	ASTM	USA	Casting
SB-505 C94700	ASME	USA	Casting
C94700	SAE	USA	Casting
CA947	SAE	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.