



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM B505 UNS C95800

Standard Specification for Copper Alloy Continuous Castings

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM B505 / 505M Copper Alloys for Continuous Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod, Bar, Tube and Shapes

Chemical Composition			Heat Treatment	
Lead	Pb %	0.030 max.	As-Cast or Solution Annealing	
Ni + Cu	Ni% + Cu%	4.000 - 5.000		
Iron	Fe %	3.500 - 4.500		
Manganese	Mn %	0.800 - 1.500		
Aluminium	Al %	8.500 - 9.500		
Silicon	Si %	0.100 max.		
Copper	Cu %	79.000 min.		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	586 min.
-	-	-	Yield Strength in Mpa	241 min.
-	-	-	Elongation in %	18 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B148 C95800	ASTM	USA	Casting
B271 C95800	ASTM	USA	Casting
SB-148 C95800	ASME	USA	Casting
SB-505 C95800	ASME	USA	Casting
C95800	SAE	USA	Casting
CACIn703	KS	Korea	Ingot and Casting
B505 C95800	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS