



Material - ASTM B86 Zamak 5

Standard Specification for Zinc and Zinc-Aluminum (ZA) Alloy Foundry and Die Castings

Group - Non-Ferrous Zinc Alloy

Sub Group - ASTM B86 Zinc and Zinc-Aluminum (ZA) Alloy Foundry and Die Castings Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|---------------|-------------------------------|-------------|
| Aluminium | Al % | 3.700 - 4.300 | | |
| Cadmium | Cd % | 0.004 max. | | |
| Chromium | Cr % | 0.020 max. | As-Cast or Aging | |
| Copper | Cu % | 0.700 - 1.200 | | |
| Iron | Fe % | 0.050 max. | | |
| Magnesium | Mg % | 0.020 - 0.060 | | |
| Manganese | Mn % | 0.060 max. | | |
| Nickel | Ni % | 0.020 max. | | • |
| Lead | Pb % | 0.005 max. | Mechanical Properties | |
| Silicon | Si % | 0.035 max. | Tensile Strength in Mpa | 328 min. |
| Tin | Sn % | 0.002 max. | Yield Strength in Mpa | 228 min. |
| Titanium | Ti % | 0.001 max. | Elongation in % | 7 min. |
| Zinc | Zn % | Balance | Reduction of Area in % | - |
| - | - | - | Hardness in HB | 91 min. |
| - | - | - | Impac <mark>t in Joule</mark> | 65 min. @RT |

| Cross Reference Table | | | | |
|-----------------------|----------|--------------------------------------|-------------------|--|
| Material | Standard | Country Grade Belong to the Industry | | |
| Zamak 5 | ANSI/AA | USA | Casting | |
| ZP5 | ISO | International | Casting | |
| Z33531 | UNS | USA | Ingot and Casting | |
| B86 Alloy 5 | ASTM | USA | Casting | |
| B86 AC41A | ASTM | USA | Casting | |
| B240 AC41A | ASTM | USA | Ingot and Casting | |
| B240 Zamak 5 | ASTM | USA | Ingot and Casting | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.