



Material - ASTM B93 AZ92A

Standard Specification for Magnesium Alloys in Ingot Form for Sand Castings

Group - Non-Ferrous Magnesium Alloy

Sub Group - ASTM B93 Magnesium Alloys in Ingot Form for Sand Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	8.500 - 9.500		
Copper	Cu %	0.200 max.		
Manganese	Mn %	0.130 - 0.350	As-Cast or Solution Treated or Fully Treated	
Nickel	Ni %	0.010 max.		
Other	Ot%	0.300 max.		
Silicon	Si %	0.200 max.		
Zinc	Zn %	1.700 - 2.300		
Magnesium	Mg %	Balance		-
-	-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	158 - 234
-	-	-	Yield Strength in Mpa	76 - 124
-	-	-	Elongation in %	1 - 6
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
Mg-Al9Zn2	ISO	International	Bar and Wire	
MC3	JIS	Japan	Casting	
B80 AZ92A	ASTM	USA	Casting	
B199 AZ92A	ASTM	USA	Casting	
B275 AZ92A	ASTM	USA	Casting	
B403 AZ92A	ASTM	USA	Casting	
B951 AZ92A	ASTM	USA	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.