

## Material - ASTM B96 C65500

Standard Specification for Copper-Silicon Alloy Plate, Sheet, Strip and Rolled Bar for General Purposes and Pressure Vessels

**Group - Non-Ferrous Copper Alloy** 

Sub Group - ASTM B96 Copper-Silicon Alloy Plate, Sheet, Strip and Rolled Bar for General Purposes and Pressure Vessels

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Plate, Sheet, Strip and Bar

Chemical Composition			Heat Treatment	
Iron	Fe %	0.800 max.		
Manganese	Mn %	0.500 - 1.300		
Ni + Co	Ni% + Co%	0.600 max.		
Lead	Pb %	0.050 max.	Normalizing or Annealing or Tempering	
Silicon	Si %	2.800 - 3.800		
Zinc	Zn %	1.500 max.		
Cu + Ag	Cu% + Ag%	Balance		
-	-	-		
-		-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	360 - 800
-	-	-	Yield Strength in Mpa	125 min.
-	-	-	Elongation in %	40 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRB	60 - 99
-	-		Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
B124 C65500	ASTM	USA	Rod, Bar and Shapes	
C65500	AS	Australia	Ingot and Casting	
B100 C65500	ASTM	USA	Plate and Sheet	
B283 C65500	ASTM	USA	Forging	
B98 C65500	ASTM	USA	Rod, Bar and Shape	
SB-98 C65500	ASME	USA	Rod, Bar and Shape	
SB-283 C65500	ASME	USA	Forging	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.