



Material - ASTM F 2527 R31537

Standard Specification for Seamless Cobalt Alloy Small Diameter Tubing for Surgical Implants

Group - Non-Ferrous Cobalt Alloys

Sub Group - ASTM F 2527 R31537 Seamless Cobalt Alloy Small Diameter Tubing for Surgical Implants Application - Intended for Valve, Pump, General Engineering, Automotive, Medical and other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.140 max.		
Chromium	Cr %	26.000 - 30.000		
Molybdenum	Mo %	5.000 - 7.000	As-Cast or Annealing	
Nickel	Ni %	1.000 max.		
Iron	Fe %	0.750 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Nitrogen	N %	0.250 max.		
Cobalt	Co %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	897 min.
-	-	-	Yield Strength in Mpa	517 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	-
-	-		Hardness in HRC	25 min.
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
F 1537 Alloy 1	ASTM	USA	Casting	
5832-12 Alloy 1	ISO	International	Casting	
7402-2	JIS	Japan	Casting	
R31537	UNS	USA	Casting	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.