

## Material - ASTM F467 C46400

## Standard Specification for Nonferrous Nuts for General Use

Group - Non-Ferrous Copper Alloy

Sub Group - ASTM F467 Nonferrous Nuts for General Use

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Nut

Chemical Composition		Heat Treatment	
Fe %	0.100 max.		
Pb %	0.200 max.		
Sn %	0.500 - 1.000		
Cu %	59.000 - 62.000	Normalizing or Anneal	ing or Tempering
Zn %	Balance		
-	-	1	
-	-		
-	-		
-	-	Mechanical Properties	
-	-	Tensile Strength in Mpa	-
-	-	Yield Strength in Mpa	344.7 - 372.3
-	-	Elongation in %	-
-	-	Reduction of Area in %	-
-	-	Hardness in HRB	55 min.
-	-	Impac <mark>t in Joule</mark>	-
	Fe % Pb % Sn % Cu % Zn % - - - - - - - - - - - - - - - - - - -	Fe %     0.100 max.       Pb %     0.200 max.       Sn %     0.500 - 1.000       Cu %     59.000 - 62.000       Zn %     Balance       -     -	Fe %       0.100 max.         Pb %       0.200 max.         Sn %       0.500 - 1.000         Cu %       59.000 - 62.000         Normalizing or Anneal         Zn %       Balance         -       -         -       Elongation in %         -

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
CuZn39Sn	IS	India	Plate	
B171 C46400	ASTM	USA	Plate and Sheet	
B283 C46400	ASTM	USA	Forging	
CZ 133	BS	British	Rod and Section	
SB-171 C46400	ASME	USA	Plate and Sheet	
SB-283 C46400	ASME	USA	Forging	
CuZn38Sn1	ISO	International	Rod and Bar	

## Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

## ONE STOP SOLUTION FOR METAL PARTS