



Material - AS/NZS 1565 C95400

Standard Specification for Copper and Copper Alloys - Ingot and Casting

Group - Non-Ferrous Copper Alloy

Sub Group - AS/NZS 1565 Copper and Copper Alloys - Ingot and Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	10.000 - 11.500	As-Cast or Solution Annealing or Annealing	
Iron	Fe %	3.000 - 5.000		
Manganese	Mn %	0.500 max.		
Nickel	Ni %	1.500 max.		
Copper	Cu %	83.000 min.		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	520 min.
			Yield Strength in Mpa	210 min.
			Elongation in %	12 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C95400	UNS	USA	Rod, Bar, Tube and Shapes
B66 C95400	ASTM	USA	Casting
B148 C95400	ASTM	USA	Casting
SB-148 C95400	ASME	USA	Casting
SB-148 Grade C	ASME	USA	Casting
CA954	SAE	USA	Casting
C95400	SAE	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.