



Material - BDS CuNi7Zn39Pb3Mn2

Standard Specification for Copper and Copper Alloy Rod

Group - Non Ferrous Copper Alloys

Sub Group - BDS CuNi7Zn39Pb3Mn2 Copper and Copper Alloy Rod

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod

Chemical Composition			Heat Treatment	
Iron	Fe %	0.300 max.		
Manganese	Mn %	1.500 - 3.000		
Nickel	Ni %	6.000 - 8.000		
Lead	Pb %	2.300 - 3.300	As Raw or Solution Heat Treated	Heat Treated
Tin	Sn %	0.200 max.		
Other	Ot %	0.200 max.		
Copper	Cu %	47.000 - 50.000		
Zinc	Zn %	Balance		-
-	-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	500 min.
-	-	-	Yield Strength in Mpa	350 min.
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HV	115 - 200
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
CuNi7Zn39Pb3Mn2	DIN	Germany	Rod	
CuNi7Zn39Pb3Mn2	ONORM	Australia	Rod	
CW400J	ONORM	Australia	Rod	
CW400J	BDS	Bulgaria	Rod	
CuNi7Zn39Pb3Mn2	CSN	Czech Republic	Rod	
CW400J	CSN	Czech Republic	Rod	
CW400J	EN	European Union	Rod	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.