

Material - BDS CuZn35Pb2

Standard Specification for Copper and Copper Alloy Rod for Free Machining Purpose Group - Non Ferrous Copper Alloys

Sub Group - BDS CuZn35Pb2 Copper and Copper Alloy Rod for Free Machining Purpose

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Rod

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.050 max.		
Iron	Fe %	0.100 max.		
Nickel	Ni %	0.300 max.	As Raw or Solution Heat Treated	
Lead	Pb %	1.600 - 2.500		eat Treated
Tin	Sn %	0.100 max.		
Other	Ot %	0.100 max.		
Copper	Cu %	62.000 - 63.500		
Zinc	Zn %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	290 min.
-	-	-	Yield Strength in Mpa	180 min.
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HV	60 - 150
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
EN 12164 CuZn35Pb2	DIN	Germany	Rod	
CW601N	BDS	Bulgaria	Rod	
CuZn35Pb2	NBN	Belgium	Rod	
CW601N	NBN	Belgium	Rod	
CuZn35Pb2	EN	European Union	Rod	
CW601N	EN	European Union	Rod	
CuZn35Pb2	DIN	Germany	Rod	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS