



## Material - BDS EN 1706 AC-41000

### Standard Specification for Aluminium and Aluminium Alloys - Castings

Group - Non-Ferrous Aluminium Alloy

Sub Group - BDS EN 1706 Aluminium and Aluminium Alloys - Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.100 max.	As-Cast	
Iron	Fe %	0.600 max.		
Magnesium	Mg %	0.450 - 0.650		
Manganese	Mn %	0.300 - 0.500		
Nickel	Ni %	0.050 max.		
Silicon	Si %	1.600 - 2.400		
Lead	Pb %	0.050 max.		
Tin	Sn %	0.050 max.		
Titanium	Ti %	0.050 - 0.200		
Zinc	Zn %	0.100 max.		
Other	Ot%	0.150 max.	Mechanical Properties	
Aluminium	Al %	Balance	Tensile Strength in Mpa	140 - 300
-	-	-	Yield Strength in Mpa	70 - 230
-	-	-	Elongation in %	3 - 10
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	50 - 95
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN AC-41000	ASME	USA	Casting
EN AC-41000	DIN	Germany	Casting
EN AC-41000	SFS	Finland	Casting
EN AC-41000	BS	British	Casting
EN AC-41000	UNE	Spain	Casting
EN AC-41000	UNI	Italy	Casting
Al Si2MgTi	ISO	International	Casting

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.