



Material - BS 1490 LM9

Standard Specification for Aluminium and Aluminium Alloy Ingots and Casting for General Engineering Purpose

Group - Non-Ferrous Aluminium Alloy

Sub Group - Aluminium Alloy BS 1490 for Ingots and Casting General Engineering Purpose

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.200 max.	As-Cast	
Magnesium	Mg %	0.200 - 0.600		
Silicon	Si %	10.000 - 13.000		
Iron	Fe %	0.600 max.		
Manganese	Mn %	0.300 - 0.700		
Nickel	Ni %	0.100 max.		
Zinc	Zn %	0.100 max.		
Lead	Pb %	0.100 max.		
Tin	Sn %	0.050 max.		
Titanium	Ti %	0.200 max.		
Other	Ot%	0.150 max.	Mechanical Properties	
Aluminium	Al %	Balance	Tensile Strength in Mpa	190 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	3 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
4635	IS	India	Ingots and Casting
G AlSi12MnMg	UNI	Italy	Ingots and Casting
G-AS12MG	UNI	Italy	Ingots and Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.