



Material - BS 2874 CA 107

Standard Specification for Copper and Copper Alloy Rods and Sections

Group - Non-Ferrous Copper Alloy

Sub Group - BS 2874 Copper and Copper Alloy Rods and Sections

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod and Section

Chemical Composition			Heat Treatment	
Aluminium	Al %	6.000 - 6.400	As-Cast	
Iron	Fe %	0.500 - 0.700		
Manganese	Mn %	0.100 max.		
Nickel	Ni %	0.100 max.		
Other	Ot%	0.500 max.		
Lead	Pb %	0.050 max.		
Silicon	Si %	2.000 - 2.400		
Tin	Sn %	0.100 max.		
Zinc	Zn %	0.400 max.		
Copper	Cu %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 520 - 630 Yield Strength in Mpa 230 - 350 Elongation in % 10 - 20 Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
AB3	BS	British	Ingot and Casting
CF301G	EN	European Union	Ingot and Casting
CF301G	BS	British	Ingot and Casting
CF301G	DIN	Germany	Ingot and Casting
CF301G	ONORM	Australia	Ingot and Casting
CuAl6Si2Fe	BS	British	Ingot and Casting
C23	BS	British	Ingot and Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.