GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 10302 2.4669 (NiCr15Fe7TiAl)

Standard Specification for Creep Resisting Steel, Nickel and Cobalt Alloys

Group - Non-Ferrous Nickel Alloys

Sub Group - BS EN 10302 2.4669 (NiCr15Fe7TiAl) Creep Resisting Steel, Nickel and Cobalt Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Steel

Chemical Composition		
Carbon	C %	0.080 max.
Silicon	Si %	0.500 max.
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.020 max.
Sulphur	S %	0.015 max.
Aluminium	Al %	0.400 - 1.000
Chromium	Cr %	14.000 - 17.000
Cobalt	Co %	1.000 max.
Copper	Cu %	0.500 max.
Iron	Fe %	5.000 - 9.000
Nb + Ta	Nb% + Ta%	0.700 - 1.200
Titanium	Ti %	2.250 - 2.750
Nickel	Ni %	70.000 min.
-	-	-
-	-	-

Heat Treatment
As-Raw or Precipitation Hardening

Mechanical Properties	
Tensile Strength in Mpa	1170 min.
Proof Strength in Mpa	790 min.
Elongation in %	-
Reduction of Area in %	15 min.
Hardness in HB	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
N07750	UNS	USA	Steel
N07752	UNS	USA	Steel
G 4902 NCF 750	JIS	Japan	Sheet and Plates
G 4901 NCF 750	JIS	Japan	Bars
2.4669	DIN	Germany	Steel
NiCr 15 Fe 7 TiAl	DIN	Germany	Steel
10269 NiCr 15 Fe 7 TiAl	EN	European Union	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.