GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 12167 CuNi12Zn30Pb1 I CW406J

Standard Specification for Copper and Copper Alloys - Profiles and Rectangular Bar for General Purposes

Group - Non-Ferrous Zinc Alloys

Sub Group - BS EN 12167 CuNi12Zn30Pb1 I CW406J Copper and Copper Alloys - Profiles and Rectangular Bar for General Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Bars

Chemical Composition		
Iron	Fe %	0.300 max.
Manganese	Mn %	0.500 max.
Nickel	Ni %	11.000 - 13.000
Lead	Pb %	0.500 - 1.500
Tin	Sn %	0.200 max.
Other	Ot %	0.200 max.
Copper	Cu %	56.000 - 58.000
Zinc	Zn %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw

Mechanical Properties	
Tensile Strength in Mpa	480 min.
Proof Strength in Mpa	330 min.
Elongation in %	10 min.
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
C79300	UNS	USA	Bars
12164 CuNi12Zn30Pb1	EN	European Union	Rods
12164 CW406J	EN	European Union	Rods
12166 CuNi12Zn30Pb1	EN	European Union	Wire
12166 CW406J	EN	European Union	Wire
12449 CuNi12Zn24	EN	European Union	Tubing
1652 CW403J	EN	European Union	Plate, Sheet and Strip

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.