



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 1676 AB-44100

Standard Specification for Aluminium and Aluminium Alloys - Alloyed Ingots for Remelting Group - Non-Ferrous Aluminium Alloy

Sub Group - BS EN 1676 for Aluminium and Aluminium Alloys - Alloyed Ingots for Remelting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|-----------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--|
| Copper | Cu % | 0.100 max. | As-Cast | |
| Iron | Fe % | 0.550 max. | | |
| Magnesium | Mg % | 0.100 max. | | |
| Manganese | Mn % | 0.550 max. | | |
| Silicon | Si % | 10.000 - 13.500 | | |
| Titanium | Ti % | 0.150 max. | | |
| Lead | Pb % | 0.100 max. | | |
| Zinc | Zn % | 0.150 max. | | |
| Other | Ot% | 0.150 max. | | |
| Aluminium | Al % | Balance | | |
| - | - | - | Mechanical Properties Tensile Strength in Mpa - Yield Strength in Mpa - Elongation in % - Reduction of Area in % - Hardness in HB - Impact in Joule - | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |

| Cross Reference Table | | | |
|-----------------------|----------|----------------|------------------------------|
| Material | Standard | Country | Grade Belong to the Industry |
| EN AB-44100 | DIN | Germany | Ingot and Casting |
| Al Si12(b) | ISO | International | Casting |
| EN AB-44100 | SFS | Finland | Ingot and Casting |
| EN AB-44100 | UNE | Spain | Ingot and Casting |
| EN AB-44100 | UNI | Italy | Ingot and Casting |
| EN AB-44100 | CSN | Czech Republic | Ingot and Casting |
| EN AB-44100 | BDS | Bulgaria | Ingot and Casting |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS