

Material - BS EN 1982 CuAlNi3Fe2-C (CC332G)

Standard Specification for Copper and Copper Alloys - Ingot and Casting

Group - Non-Ferrous Copper Alloy

Sub Group - BS EN 1982 Standard Specification for Copper and Copper Alloys - Ingot and Casting Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Magnesium	Mg %	0.050 max.		
Lead	Pb %	0.100 max.		
Silicon	Si %	0.200 max.	As-Cast	
Tin	Sn %	0.200 max.		
Zinc	Zn %	0.500 max.		
Nickel	Ni %	1.500 - 4.000		
Manganese	Mn %	2.000 max.		
Iron	Fe %	1.000 - 3.000		
Aluminium	AI %	8.500 - 10.500	Mechanical Properties	
Copper	Cu %	80.000 - 86.000	Tensile Strength in Mpa	500 min.
-	-	-	Yield Strength in Mpa	180 min.
-	-	-	Elongation in %	18 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HBW	100 min.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS