



## Material - BS EN 1982 CuSn5Zn5Pb5-B (CB491K)

Standard Specification for Copper and Copper Alloys - Ingot and Casting

Group - Non-Ferrous Copper Alloy

Sub Group - BS EN 1982 Standard Specification for Copper and Copper Alloys - Ingot and Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.010 max.	As-Cast	
Iron	Fe %	0.030 max.		
Sulphur	S %	0.100 max.		
Antimony	Sb %	0.250 max.		
Silicon	Si %	0.010 max.		
Nickel	Ni %	2.000 max.		
Phosphorus	P %	0.100 max.		
Lead	Pb %	4.000 - 6.000		
Zinc	Zn %	4.000 - 6.000		
Tin	Sn %	4.000 - 6.000		
Cu + Ni	Cu%+Ni%	83.000 - 87.000	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	200 min.
-	-	-	Yield Strength in Mpa	90 min.
-	-	-	Elongation in %	13 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HBW	60 min.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CC491K	DIN	Germany	Ingot and Casting
CuSn5Zn5Pb5-C	DIN	Germany	Ingot and Casting
CC491K	MSZ	Hungary	Ingot and Casting
CuSn5Zn5Pb5-C	MSZ	Hungary	Ingot and Casting
CC491K	AFNOR NF	France	Ingot and Casting
CuSn5Zn5Pb5-C	AFNOR NF	France	Ingot and Casting
CC491K	UNE	Spain	Ingot and Casting

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.