

Material - BS EN 1982 CuZn33Pb2-C (CC750S)

Standard Specification for Copper and Copper Alloys - Ingot and Casting

Group - Non-Ferrous Copper Alloy

Sub Group - BS EN 1982 Standard Specification for Copper and Copper Alloys - Ingot and Casting Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Ingot and Casting

| Chemical Composition | | | Heat Treatment | |
|----------------------|---------|-----------------|-------------------------------|----------|
| Nickel | Ni % | 1.000 max. | | |
| Lead | Pb % | 1.000 - 3.000 | | |
| Tin | Sn % | 1.500 max. | As-Cast | |
| Aluminium | Al % | 0.100 max. | | |
| Iron | Fe % | 0.800 max. | | |
| Manganese | Mn % | 0.200 max. | | |
| Phosphorus | P % | 0.050 max. | | |
| Silicon | Si % | 0.050 max. | | |
| Cu + Ni | Cu%+Ni% | 63.000 - 67.000 | Mechanical Properties | |
| Zinc | Zn % | Balance | Tensile Strength in Mpa | 180 min. |
| - | - | - | Yield Strength in Mpa | 70 min. |
| - | - | - | Elongation in % | 12 min. |
| - | - | - | Reduction of Area in % | - |
| - | - | - | Hardness in HBW | 45 min. |
| - | - | - | Impac <mark>t in Joule</mark> | - |

| Cross Reference Table | | | | |
|-----------------------|----------|----------------|------------------------------|--|
| Material | Standard | Country | Grade Belong to the Industry | |
| CB750S | EN | European Union | Ingot and Casting | |
| CB750S | DIN | Germany | Ingot and Casting | |
| CB750S | UNI | Italy | Ingot and Casting | |
| CB750S | BS | British | Ingot and Casting | |
| CAC202 | JIS | Japan | Casting | |
| CuZn33Pb2-B | PN | Poland | Ingot and Casting | |
| CuZn33Pb2-B | AFNOR NF | France | Ingot and Casting | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS