

Material - BSI BS1400 LG4 CuSn7Pb3Zn3

Standard Specification for Copper Alloy and High Conductivity Conductivity Copper Casting

Group - Non-Ferrous Copper Alloy

Sub Group - BSI BS1400 Copper Alloy and High Conductivity Conductivity Copper Casting Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Tin	Sn %	6.000 - 8.000		
Zinc	Zn %	1.500 - 3.000		
Lead	Pb %	2.500 - 3.500	As-Cast	
Nickel	Ni %	2.000 max.		
Iron	Fe %	0.200 max.		
Aluminium	Al %	0.010 max.		
Antimony	Sb %	0.250 max.		
Arsenic	As %	0.150 max.		
Fe + As + Sb	Fe+As+Sb	0.400 max.	Mechanical Properties	
Silicon	Si %	0.010 max.	Tensile Strength in Mpa	250 min.
Bismuth	Bi %	0.050 max.	Yield Strength in Mpa	130 min.
Other	Ot%	0.700 max.	Elongation in %	16 min.
Copper	Cu %	Balance	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
-	-	·	-		
-	-	-	-		
-	-	-	-		
-	-	-	-		
-	-	-	-		
-	-	-	-		
-	-	-	-		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.