

Material - BSI BS1400 LPB1 CuSn7PbP

Standard Specification for Copper Alloy and High Conductivity Conductivity Copper Casting

Group - Non-Ferrous Copper Alloy

Sub Group - BSI BS1400 Copper Alloy and High Conductivity Conductivity Copper Casting Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Tin	Sn %	6.500 - 8.500		
Zinc	Zn %	2.000 max.		
Lead	Pb %	2.000 - 5.000	As-Cast	
Phosphorus	Р%	0.300 min.		
Nickel	Ni %	1.000 max.		
Antimony	Sb %	0.250 max.		
Sulphur	S %	0.100 max.		
Other	Ot%	0.500 max.		
Copper	Cu %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	190 min.
-	-	-	Yield Strength in Mpa	80 min.
	-	-	Elongation in %	3 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardne <mark>ss in BHN</mark>	-
-	-	-	Impa <mark>ct in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
CuSn8Pb2	ISO	International	Casting	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS