

## Material - BSI BS1400 PB2 CuSn11PbP

Standard Specification for Copper Alloy and High Conductivity Conductivity Copper Casting

**Group - Non-Ferrous Copper Alloy** 

Sub Group - BSI BS1400 Copper Alloy and High Conductivity Conductivity Copper Casting Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Tin	Sn %	11.000 - 13.000		
Zinc	Zn %	0.300 max.		
Lead	Pb %	0.500 max.	As-Cast	
Phosphorus	Р%	0.150 - 0.600		
Nickel	Ni %	0.500 max.		
Iron	Fe %	0.100 max.		
Aluminium	Al %	0.010 max.		
Silicon	Si %	0.020 max.		
Sulphur	S %	0.100 max.	Mechanical Properties	
Other	Ot%	0.200 max.	Tensile Strength in Mpa	220 min.
Copper	Cu %	Balance	Yield Strength in Mpa	130 min.
	-	-	Elongation in %	5 min.
	-	-	Reduction of Area in %	-
-	-	-	Hardne <mark>ss in BHN</mark>	-
-	-	-	Impa <mark>ct in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
907C	AS	Australia	Ingot and Casting	
C90810	AS	Australia	Ingot and Casting	
CuSn11P	ISO	International	Ingot and Casting	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

## Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

## **ONE STOP SOLUTION FOR METAL PARTS**