



Material - CSN 42 4336 AlSi12NiCuMg

Standard Specification for Aluminium alloy for Castings

Group - Non-Ferrous Aluminium Alloy

Sub Group - CSN 42 4336 Aluminium alloy for Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.800 - 1.500	As-Cast	
Iron	Fe %	0.500 max.		
Magnesium	Mg %	0.900 - 1.300		
Manganese	Mn %	0.300 max.		
Nickel	Ni %	8.000 - 1.300		
Silicon	Si %	11.000 - 13.000		
Titanium	Ti %	0.200 max.		
Zinc	Zn %	0.150 max.		
Aluminium	Al %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	140 - 220
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	0.5 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	80 - 90
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
AC8A	JIS	Japan	Casting
A-S12UN	AFNOR NF	France	Casting
AA319	AS	Australia	Ingot and Casting
319	AS	Australia	Ingot and Casting
LM13	BS	Czech Republic	Casting
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.