



Material - CSN CuSn7Zn4Pb7-C

Standard Specification for Copper and Copper Alloy Castings

Group - Non Ferrous Copper Alloys

Sub Group - CSN CuSn7Zn4Pb7-C Copper and Copper Alloy Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Silicon	Si %	0.010 max.	As Cast	
Lead	Pb %	5.000 - 8.000		
Iron	Fe %	0.200 max.		
Tin	Sn %	6.000 - 8.000		
Zinc	Zn %	2.000 - 5.000		
Nickel	Ni %	2.000 max.		
Aluminium	Al %	0.010 max.		
Sulphur	S %	0.100 max.		
Antimony	Sb %	0.300 max.		
Nickel	Ni %	2.000 max.		
Cu + Ni	Cu% + Ni%	81.000 - 85.000	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	230 min.
-	-	-	Yield Strength in Mpa	120 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	60 min.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuSn7Zn4Pb7-C	DIN	Germany	Casting
CuSn7Zn4Pb7-C	ONORM	Australia	Casting
CC493K	ONORM	Australia	Casting
CuSn7Zn4Pb7-C	BDS	Bulgaria	Casting
CC493K	BDS	Bulgaria	Casting
CuSn7Zn4Pb7-C	SFS	Finland	Casting
CuSn7Zn4Pb7-C	MSZ	Hungary	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +91846916029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.