



## Material - DIN 1.3928

## **Standard Specification for Nickel and Nickel Alloy Castings**

**Group - Non-Ferrous Nickel Alloys** 

Sub Group - DIN 1.3928 Nickel and Nickel Alloy Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

**Grade Belongs to the Industry - Casting** 

Chemical Composition			Heat Treatment	
Carbon	C %	0.020 max.		
Silicon	Si %	0.200 max.		
Manganese	Mn %	1.000 max.		
Nickel	Ni %	50.000 - 52.000	As-Cast or Annealing or Age Hardning	or Age Hardning
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	440 - 640
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table					
Material	Standard	Country	Gr <mark>ade Belong</mark> to the Industry		
Ni52	SEW	Germany	Casting		
-	_	-	-		
-	-	-			
-	-	-	-		
-	-	-	-		
-	-		-		
-	-		-		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.