



Material - DIN 1706 EN AC-51300

Standard Specification for Aluminium Alloy and Aluminium Alloys

Group - Non-Ferrous Alumium Alloy

Sub Group - DIN 1706 Aluminium Alloy and Aluminium Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.100 max.	As-Cast	
Magnesium	Mg %	4.300 - 6.800		
Silicon	Si %	0.550 max.		
Iron	Fe %	0.550 max.		
Manganese	Mn %	0.450 max.		
Titanium	Ti %	0.200 max.		
Zinc	Zn %	0.100 max.		
Beryllium	Be %	0.005 max.		
Other	Ot%	0.150 max.	Mechanical Properties	
Aluminium	Al %	Balance	Tensile Strength in Mpa	150 - 180
-	-	-	Yield Strength in Mpa	80 - 100
-	-	-	Elongation in %	3 - 14
-	-	-	Reduction of Area in %	-
-	-		Hardness in HB	55 - 70
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
LM5	BS	British	Ingot and Casting	
5230	IS	India	Casting	
EN AC-51300	AFNOR NF	France	Ingot and Casting	
EN AC-51300	EN	European Union	Ingot and Casting	
EN AC-51300	ONORM	Australia	Ingot and Casting	
EN AC-51300	BDS	Bulgaria	Ingot and Casting	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.