



Material - DIN 2.2141

Standard Specification For Zinc and Zinc Alloy Castings

Group - Non-Ferrous Zinc Alloys

Sub Group - DIN 2.2141 Zinc and Zinc Alloy Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	3.700 - 4.100	As-Cast	
Copper	Cu %	0.500 - 1.000		
Magnesium	Mg %	0.030 - 0.060		
Lead	Pb %	0.003 max.		
Cadmium	Cd %	0.003 max.		
Tin	Sn %	0.001 max.		
Iron	Fe %	0.020 max.		
Zinc	Zn %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 330 min. Yield Strength in Mpa 250 min. Elongation in % 5 min. Reduction of Area in % - Hardness in HB 92 min. Impact in Joule 58 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
ZP5	DIN	Germany	Casting
Alloy B	BS	British	Casting
G-ZnAl4Cu1	UNI	Italy	Ingot
ZnAl4Cu1	UNE	Spain	Ingot
ZnAl4Cu1	NS	Norway	Ingot
ZnAl4Cu1	SS	Sweden	Ingot
B 240 AC41A	ASTM	USA	Ingot and Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.