

Material - DIN 2.2161.01

Standard Specification for Zinc and Zinc Alloy Die Castings

Group - Non-Ferrous Zinc Alloys

Sub Group - DIN 2.2161.01 Zinc and Zinc Alloy Die Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	5.600 - 6.000		
Copper	Cu %	1.200 - 1.600		
Magnesium	Mg %	0.005 max.		
Pb + Cd	Pb% + Cd%	0.006 max.	As-Cast	
Tin	Sn %	0.001 max.		
Iron	Fe %	0.050 max.		
Zinc	Zn %	Balance		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	180 - 230
-	-	-	Yield Strength in Mpa	150 - 180
-	-	-	Elongation in %	1 - 3
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	80 - 90
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	ntry Grade Belong to the Industry	
ZP6	DIN	Germany	Casting	
ZnAl6Cu1	UNE	Spain	Casting	
2.2161	DIN	Germany	Ingot and Casting	
2.2161.02	DIN	Germany	Casting	
GB-ZnAl6Cu1	DIN	Germany	Ingot and Casting	
GK-ZnAl6Cu1	DIN	Germany	Ingot and Casting	
G-ZnAl6Cu1	DIN	Germany	Ingot and Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS