



Material - DIN 2.4017

Standard Specification for Refined Nickel Alloy Castings

Group - Non-Ferrous Nickel Alloys

Sub Group - DIN 2.4017 Refined Nickel Alloy Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Chemical Composition		
Carbon	C %	0.015 max.	Zinc	Zn %	0.002 max.
Phosphorus	P %	0.002 max.	Ni + Co	Ni% + Co%	99.950 min.
Cobalt	Co %	0.100 max.	-	-	-
Copper	Cu %	0.005 max.	-	-	-
Iron	Fe %	0.020 max.	-	-	-
sulphur	S %	0.0025 max.	Heat Treatment		
Silver	Ag %	0.0005 max.	As-Cast or Annealing or Age Hardning		
Arsenic	As %	0.001 max.	Mechanical Properties		
Bismuth	Bi %	0.0005 max.	Tensile Strength in Mpa	-	
Lead	Pb %	0.001 max.	Yield Strength in Mpa	-	
Antimony	Sb %	0.001 max.	Elongation in %	-	
Selenium	Se %	0.001 max.	Reduction of Area in %	-	
Tin	Sn %	0.0005 max.	Hardness in BHN	-	
Tellurium	Te %	0.0005 max.	Impact in Joule	-	
Titanium	Ti %	0.0005 max.			

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
H-Ni99,95	DIN	Germany	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.