

Material - DIN 2.4025

Standard Specification for Refined Nickel Alloy Castings

Group - Non-Ferrous Nickel Alloys

Sub Group - DIN 2.4025 Refined Nickel Alloy Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 max.		
Cobalt	Co %	1.500 max.		
Copper	Cu %	0.300 max.		
Iron	Fe %	0.100 max.	As-Cast or Annealing or Age Hardning	Age Hardning
Sulphur	S %	0.050 max.		
Ni + Co	Ni% + Co%	99.000 min.		
-	-	-		
-	-	-		
-	_	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table					
Material	Standard	Country	Gr <mark>ade Belong</mark> to the Industry		
Ni 9900	ISO	International	Casting		
H-Ni99	DIN	Germany	Casting		
-	-	-	-		
-	-	-	-		
-	-	-	-		
-	-	-	-		
-	-		-		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS